

<b>Product Name</b>	Slammers Rigid/PVC Conduit Spacer 1"
<b>Brand</b>	<b>RACK-A-TIERS</b>
<b>Part Number</b>	35100.RCS
<b>UPC</b>	625912351011

Product Weight and Package Dimensions	
<b>Product Weight</b>	2.23lbs
<b>Product Dimensions (L x W x H)</b>	1"
<b>Product Package Dimensions (L x W x H)</b>	10" X 14" X 5"

<b>Product Material</b>	ABS Plastic
<b>Product Type</b>	Conduit Spacers
<b>Colour</b>	Blue
<b>Quantity</b>	50 pieces per bag

**Product Features**  
**Lock your rigid or PVC conduit in place during concrete pours**

- Made in the USA.
- Available in ¾" and 1" sizes to fit Schedule 40 Metal or PVC.
- **PRECISION** – Take pride in your work by using the Slammers Cap & Spacer system for an install that will make others jealous. Designed specifically with 4-square boxes in mind, you can be sure you'll get the perfect fit every time.
- **SPEED** – Save time with Slammers! Trying to get precise alignment with duct tape or tie wire can waste hours over the course of a job. Slammers' one-step install allows for consistent, predictable install times.
- **SIMPLE** – These conduit and PVC spacers are even easier to use than tie wire. Just slam them on and you're ready for the concrete pour.
- **DURABLE** – Slammers are made of high-quality ABS plastic that can withstand even the harshest job sites and elements. The durable material prevents cracking or breaking, and you never have to worry about them peeling off like duct tape.

General Information			
<b>General</b>			
Ashland Product Code	* 4030501		
Material Status	* Commercial: Active		
Availability	* North America		
Test Standards Available	* ASTM		
Recycled Content	* No		
Features	* Easy flowing , Heat and impact resistance, RoHS compliant		
Forms	* Pellets		
Processing Method	* Injection		
Properties			
	Nominal Value	Unit	Test Method
Melt Volume -Flow Rate (MVR) (230 °C/3.8 kg)	4.8	cm <sup>3</sup> /10min	ASTM D1238
Melt Volume-Flow Rate (MVR ) (220°C/10 kg)	19	cm <sup>3</sup> /10min	ASTM D1238
Density	1.04	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>			
	Nominal Value	Unit	Test Method
Tensile Modulus	333,000	psi	ASTM D638
Tensile Strength@ Yield	6,520	psi	ASTM D638
Flexural Modulus	333,000	psi	ASTM D790
Flexural Strength	9,430	psi	ASTM D790
<b>Impact</b>			
	Nominal Value	Unit	Test Method
Notched Izod (73°F)	5.6	ft-lb/in	ASTM D256
Charpy Impact Strength	*	kJ/m <sup>2</sup>	ISO 179
<b>Hardness</b>			
	Nominal Value	Unit	Test Method
Rockwell	103	R	ASTM D785
<b>Thermal</b>			
	Nominal Value	Unit	Test Method
Vicat, A/2 (50 deg, C/h, 50N)	204	°F	ASTM D1525
Deflection Temperature of Plastic @ 66 psi	195	°F	ASTM D648
Deflection Temperature of Plastic @ 264 psi	172	°F	ASTM D648
Optical	Nominal Value	Unit	Test Method
	*		
<b>UL Information</b>			
	Nominal Value	Unit	Test Method
Flammability Rating @ 0.031	HB	---	UL 94
Flammability Rating @ 0.059	HB	---	UL 94
Flammability Rating @ 0.118	HB	---	UL 94

**Suggested Applications**  
Rigid thin walled containers, sports and leisure , toys, Housewares, Molded caps and closures

**Other Properties**

**Compliance**  
Hival ABS HG6 Natural meets the requirements of the "Federal Food, Drug and Cosmetic Act" and all applicable "Food Additive Regulations" including 21 CFR 181.32 "Acrylonitrile copolymers and resins". The products may only be used in repeated use applications and not in contact with food containing alcohol. Compliance to extractive limitations is the responsibility of the article manufacturer (21 CFR 181.32(b)).

